



### CHARCOAL 65 C

The Charcoal 65 C tinted automotive window film confers a touch of aesthetic embellishment to any vehicle, whilst ensuring moderate privacy from prying eyes.



SOLAR SCREEN® Warranty  
**5 YEARS**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**

### WIDTHS AVAILABLE:

↔ **152 cm**

### TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	39 %
Reflection of external visible light	7 %
Reflection of internal visible light	7 %
Total solar energy rejected	28 %
Total solar energy rejected 2	28 %
Solar ratio :	
Solar energy reflection	6 %
Solar energy absorption	39 %
Solar energy transmission	55 %
Reduction in Solar Glare	60 %
g-value	0.66
u-value	-
Shading coefficient	
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	25 µ

Colour : BLACK

### CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. PS adhesive, glass polymerization within 15 days
4. Protection release liner, disposable after installation



### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. sun pose 0808 or 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

*Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time.*

### INSTALLATION ADVICE

Vertical installation and on standard glass surface\*

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✗
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	✗

✓Yes ! Caution ✗No

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.