





GREY 30 UVC

Carefully applied to any kind of glazing, Grey 30 UVC films are specially designed to filter out harmful UV rays, as well as a considerable amount of infrared and visible light. This film will protect items and furnishings exposed to Sun or Moon light from fading and premature ageing.



SOLAR SCREEN® Warranty **5 YEARS**



Storage from -5°C to +40°C **3 YEARS**



REACH RoHS compliant



RESPECTED

WIDTHS AVAILABLE:



152 cm

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	0.5 %
Visible light transmission	73 %
Reflection of external visible light	8 %
Reflection of internal visible light	8 %
Total solar energy rejected	20 %
Total solar energy rejected 2	21 %
Solar ratio:	
Solar energy reflection	9 %
Solar energy absorption	16 %
Solar energy transmission	75 %
Reduction in Solar Glare	17 %
g-value	0.79
u-value	42221
Shading coefficient	0.8

INSTALLATION ADVICE

Valid for vertical glazed surfaces and areas not exceeding 2.5 m2

Clear single pane	~
Tinted single pane	~
Reflective tinted single pane	~
Clear double pane	~
Tinted double pane	~
Reflective tinted double pane	~
Gas-filled double pane - Low E	~
STADIP clear double pane	~
STADIP INT. clear double pane	~

✓Yes	Caution	× No


Installation type	Internal application
Roll length	30,5 m
PET / PVC composition	PET
Thickness	50 μ

Colour: LIGHT GREY

CONSTRUCTION

- 1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning

 2. Dyed polyester without optical distortion
- **3.** Bonding adhesive
- **4.** High optical quality polyester
- **5.** PS adhesive, glass polymerization within 15 days
- **6.** Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. sun pose 0808 or 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

 $Non-contractual\ data, SOLAR\ SCREEN \circledR\ reserves\ the\ right\ to\ modify\ the\ composition\ of\ its\ films\ at\ any\ time.$